Verosol

710 Aspect



Flame retardant blockout fabric for complete privacy

Features

- Inherently flame retardant fabric suitable for commercial applications
- Plain woven with a soft touch opaque flocked backing for a uniform look
- Designed for maximum room darkening and total privacy
- Suitable for Roller Blinds, Roman Blinds and Panel Glides

Care Instructions

For regular maintenance, use a soft feather duster or vacuum-clean with a soft brush in a low setting. If commercial spot cleaners are used, they must first be tested and allowed to dry on an inconspicuous area to ensure compatibility.

For more information visit verosol.com.au or call 1800 721 404



710 Aspect

Fabric Density	Blockout		Pattern	Plain Weave					
Composition	100% Polyester with Foamed Flocked Acrylic Coating [no fibreglass content] - PVC Free								
Weight	410gsm ± 5%	•••••••		Warp 22 / cm					
Thickness	0.70mm ± 5%	••••••	···· Construction	Warp 10 / cm					
Width	3000mm		Dimensional Change	- 0.7% max					
Colour Fastness	≥ 5 [ISO 105-B02]		Opacity	AS2663.3-1999					
Flame Retardancy [AS/NZS 1530.3-1999]	Ignitability Index	0 Range [0-20]							
	Spread of flame Index	0 Range [0-10]							
	Heat evolved Index	0 Range [0-10]	•••••••••••••••••••••••••••••••••••••••						
	Smoke developed Index	6 Range [0-10]	•••••••••••••••••••••••••••••••••••••••						
[International]	NFPA 701 (USA)	••••••							
Suitable Products	Roller Blinds	Roman Blinds	Panel Glides						
••••••	• • • • • • • • • • • • • • • • • • • •	••••••••••••••••••••••••••••••••••	••••••••••••••••••••••••••••••	•••••••••••••••••••••••••••••••••••••••					

Colour Range							
1500 White	2000 Gypsum	4000 Paraffin	5000 Pale Stone	5500 Desert Sand	7000 Eiffel Tower	8000 Accord	8400 Armour

9000 Ebony 8500 Domino

© Copyright 2021 Verosol Australia [ABN 36 006 221 003] Updated September 2023 Information supplied was current at time of printing. Please refer to Warranty Terms & Conditions at www.verosol.com.au for more information. All presented data calculated in WIS 3.0.1 (Advanced Windows Information System) with spectral data. Specifications and other data are based on information available at the time of preparation of this document and are subject to production tolerances and/or change without prior notice. Flame retardancy information is sourced from AWTA testing results [AS/NZS 1530.3-1999]. Please note that test results may vary slightly depending on fabric colour. Note: All colours are representative only, please request an A4 sample for accurate colour representation at www.verosol.com.au.