
745 Hemisphere 5%

Semi Transparent





A unique weave combining a functional solution for solar protection with a stylish textured appearance

Features

- Provides privacy without comprimising the view
- · Allows for a moderate flow of fresh air
- Reduces glare in direct sunlight, and provides UV protection
- Reduces heat transmission

Care Instructions

Regularly wipe clean with a solution of mild soap and water using a soft damp cloth or soft bristle brush. Rinse thoroughly with fresh water and allow the fabric to dry completely before it is rolled up.

For more information visit verosol.com.au or call 1800 721 404







745 Hemisphere 5%

Semi Transparent

Fabric Density	Semi Transparent		Protection	Mildew & Salt Water Resistant				
Composition	30% Polyester / 70% PVC	• • • • • • • • • • • • • • • • • • • •	Tear Strength	Warp 240N / Weft 190N				
Weight	530gsm	• • • • • • • • • • • • • • • • • • • •	Tensile Strength	Warp 2700N / Weft 2400N				
Thickness	0.75mm	• • • • • • • • • • • • • • • • • • • •	Construction	37 x 35 weave (2x2)				
Width	3200mm							
Flame Retardancy [AS/NZS 1530.3-1999]	Ignitability Index	16 Range [0-20]	Complies with BCA General requirements					
	Spread of flame Index	0 Range [0-20]	• • • • • • • • • • • • • • • • • • • •					
	Heat evolved Index	3 Range [0-20]	• • • • • • • • • • • • • • • • • • • •					
	Smoke developed Index	7 Range [0-20]	• • • • • • • • • • • • • • • • • • • •					
Certification	Greenguard	Oeko-tex 100	ISO 9001	ISO 14001				
	Ecospecifier	• • • • • • • • • • • • • • • • • • • •	• • • • • • • • • • • • • • • • • • • •					
Suitable Products	External Roller Blinds	• • • • • • • • • • • • • • • • • • • •	•••••••••••					

Fabric colour code	1000	1500	2000	3000	4000	5000	6000	7000	8000	9000
Solar transmittance	22%	9%	7%	7%	6%	7%	6%	6%	6%	7%
Solar reflectance outside	64%	16%	8%	8%	10%	9%	6%	5%	4%	4%
Solar absorptance	14%	75%	85%	85%	84%	84%	88%	89%	89%	89%
Luminous transmittance [VLT]	21%	15%	11%	12%	45%	10%	10%	10%	10%	10%
UV transmittance	7%	6%	6%	6%	7%	6%	6%	6%	6%	6%
Openness factor	5%	5%	5%	5%	5%	5%	5%	5%	5%	5%

Colour Range

