

## 890 SilverScreen Originals

Blockout Metallised



Flame Retardant



Roller Blinds

*Flame retardant solution with superior heat and light control*

### Features

- Part of the Verosol Core Collection - metallised fabrics developed in Europe, to the highest quality standard
- Designed for maximum room darkening and total privacy
- Superior heat and glare control, excellent energy efficient solution
- Woven from 100% Polyester and is flame retardant
- Oeko-Tex and Greenguard Gold certified
- Suitable for Roller Blinds

### Care Instructions

Verosol fabrics are anti-static and therefore dust repellent. For regular maintenance, use a soft feather duster or vacuum-clean with a soft brush in a low setting.

For more information visit [verosol.com.au](http://verosol.com.au) or call **1800 721 404**



# 890 SilverScreen Originals

## Blockout Metallised

Fabric Density	Blockout	Anti-Static	Yes		
Composition	100% Polyester	PVC Free	Phthalate Free	Formaldehyde Free	Antimicrobials Free
Weight	325gsm ± 5%				
Thickness	0.33mm ± 5%				
Width	3000mm ± 50mm				
Colour Fastness	> 5 ISO Standard 105-B02				
Flame Retardancy [AS/NZS 1530.3-1999]	Ignitability Index	0	Range [0-20]		
	Spread of flame Index	0	Range [0-10]		
	Heat evolved Index	0	Range [0-10]		
	Smoke developed Index	5	Range [0-10]		
[AS/NZS 3837-1998]	Classification Group 2				
[International]	DIN 4102 B1 (D)   BS5867-2 (UK)   NFPA 701 (USA)				
Aluminium Adhesion	ISO 2409 Classification 0	IR Emissivity Metal Side	0.29		
Certifications	Greenguard Gold	Oeko-Tex 100 Class IV	ISO 9001:2015		
	ISO 14001:2015	REACH	ROHS2		
Suitable Products	Roller Blinds				

Fabric colour code	All Colours
Solar transmittance	0%
Solar reflectance outside	70%
Solar absorptance	30%
Luminous transmittance [VLT]	0%
UV transmittance	0%
Openness factor (nominal)	0%

### Glazing Type - Single 4mm Clear Glass

Visible light transmittance	0%
G-value / Solar heat gain coefficient	22%
Shading coefficient	25%
U-value (W/m <sup>2</sup> K)	2.1

### Glazing Type - High Performance Glazing

Visible light transmittance	0%
G-value / Solar heat gain coefficient	16%
Shading coefficient	18%
U-value (W/m <sup>2</sup> K)	0.8

### Colour Range

